



# FEINGOSIL PA 320T (A+B)

TECHNICAL DATA SHEET N°443

REVISION DATE 01.07.2016

REVISION: 6.0 (EN)

## **PROPERTIES:**

CHEMICAL CHARACTERIZATION	: Addition-cured RTV-2
ODOUR	: Odourless
SOLUBILITY	: Not mixable in water, dispersible in most of solvents
ASPECT PART A	: Fluid/transparent
ASPECT PART B	: Fluid/ transparent
SPECIFIC GRAVITY	: 1.01 g/cm <sup>3</sup>
VISCOSITY	: 500 mPa·s

## **CURING PROPERTIES:**

MIX RATIO	: 100:100
WORKING TIME	: 40 minutes
SETTING TIME	: 16 ÷ 24 hours
HARDNESS 24 h	: 18 Shore A
SHRINKAGE (after 24 h)	: < 0.1 %

The data given are typical values which are not intended for use in preparing specifications. The information given here is based on our present state of knowledge and is published without obligation on our part. Test has done at 23°C and 50% of RH.

This new data sheet replaces all previously printed documentation.