



THIXO PA

TECHNICAL DATA SHEET N°275

REVISION DATE 01.07.2016

REVISION: 6.0 (EN)

PROPERTIES:

ASPECT	: Liquid
CHEMICAL CHARACTERIZATION	: Thickening agent for RTV-2
COLOUR/ODOUR	: Beige/Odourless
VISCOSITY	: 1000 MPa·s
MIX RATIO	: 2 ÷ 4 % on the weight of the RTV-2

HOW TO USE:

This product is used when you want to apply vertically the silicone rubber. It can be used with all Feingosil Series 300. First at all add the catalyst to the base, then add 2 ÷ 4 % of THIXO PA on the weight of the silicone rubber. Mix for 3-5 minutes.

You get a very viscous mass, which can be applied in vertical. With a brush or a spatula, spread the thixotropic silicone rubber to form a layer of 5-10 mm. If necessary, repeat after 4-6 hours (before the silicone rubber is completely cured) to obtain a mould with good strength (20-40 mm).

STORAGE AND SHELF LIFE:

The product, when stored under appropriate conditions, is stable and usable for **twelve months**. Beyond this date, Feinchimica no longer guarantees that the products meet sales specifications. We suggest to keep the products in their original packaging, well-closed at a temperature between +7°C and +27°C, in well-aired places.

SAFETY INFORMATION:

This product doesn't contain toxic or corrosive compounds. It doesn't require special safety measures during handling. Follow normal safety precautions taken in the case of contact with chemicals. See, however, the safety data sheet before use.

The data given are typical values which are not intended for use in preparing specifications. The information given here is based on our present state of knowledge and is published without obligation on our part. Test has done at 23°C and 50% of RH.

This new data sheet replaces all previously printed documentation.